



10840 Thornmint Road, Suite 107, San Diego, CA 92127-2404  
 phone: 858-451-3313 fax: 858-451-3314  
[info@symcoat.net](mailto:info@symcoat.net)  
<http://www.symcoat.net>

## Sulfuric Anodize MIL-A-8625F Spec

<p>Color will vary with alloy. Aluminum with low alloying elements will show practically no color change. Best coating on aluminum for dyeing. Can be dyed practically any color or shade (black, blue, red, ect.) Minimum weight type II coatings.</p> <p>Class 1 - 600 milligrams/sq.ft. Class 2 - 2500 milligrams/sq.ft.</p> <p>NOTE: <i>For wrought 2000 series and castings with 1% or greater copper min. ctg.. wt.. Shall be 1400 milligrams/sq.ft.</i></p>	<p>Type II</p> <p>Class 1</p> <p>Class 2</p>	<p>.00005-.0010"</p>	<p>All aluminum alloys, but do not use where solution will entrap</p> <p>FED-STD-No.595 may be used as a guide for specifying color (approximate comparison only).Non-dyed.</p> <p>Dyed.</p>
--	--	----------------------	--